RUNNING TRACKS

POLTRACK SEALED SPRAYCOAT

Synthetic outdoor system for running tracks.


It is applied on fine asphalt or smooth, waterproof concrete, without rising humidity issues. Consists of a first base layer mixed at site, mixture of RECYCLED RUBBER 858 SBR granules and the polyurethane binder POLAPLAST P13, then a second layer (sealing layer), a polyurethane pore filler, POLYSPORT STUCCO 1050 and then a third layer, spray coat, is applied at site which consists of EPDM 856 (0.5-1.5mm) and the spraycoat, colored polyurethane binder POLAPLAST P12.

Priming with **POLAPLAST P10** precedes the application.



Steps:

- 1. POLAPLAST P10 Polyurethane primer.
 - Applied by airless sprayer or brush.
- 2. Mixture of POLAPLAST P13 and RECYCLED RUBBER 858 SBR granules.
 - Applied by paving machine.
- 3. POLYSPORT STUCCO 1050 Polyurethane, elastic, two-component pore filler.
 - Used for sealing porous prefabricated subfloor of sports floorings such as **ISOPOL 854** or wet-pour cushion shockpads. Applied by flat trowel.
- 4. Mixture of POLAPLAST P12 and EPDM 856.
 - Applied by spraying machine in two crossings.



Description	Consumption
POLAPLAST P10 - Polyurethane primer.	0.15-0.2kg/m ²
BASE LAYER	
POLAPLAST P13 - One-component, polyurethane binder.	1.2kg/m²
RECYCLED RUBBER 858 in granulometry of 1-4mm.	6kg/m²
SEALING LAYER	
POLYSPORT STUCCO 1050 - Polyurethane, elastic, two-component pore filler.	2kg/m ² for 2 layers
SPRAY LAYER	
POLAPLAST P12 - Colored, two-component polyurethane spray coating.	1.35kg/m²
EPDM 856 in granulometry of 0.5-1.5mm.	0.9kg/m²