

# RUNNING TRACKS

## POLTRACK SPRAYCOAT

Synthetic outdoor system for running tracks in total thickness of 13.5mm.

It is applied on fine asphalt or smooth, waterproof concrete, without rising humidity issues, in two basic layers. The first, base layer, is mixed at site, and consists of the polyurethane binder **POLAPLAST P13** and **RECYCLED RUBBER 858**, SBR granules. The second layer, spray layer, is applied at site and consists of the colored polyurethane spray coating **POLAPLAST P12** and **EPDM 856**.

**Certified system by WORLD ATHLETICS and according to EN 14877.**



### Steps:

- POLAPLAST P10 - Polyurethane primer.**  
Applied by airless sprayer or brush.
- Mixture of POLAPLAST P13 and RECYCLED RUBBER 858 in granulometry of 1-4mm.**  
Applied by paving machine.
- Mixture of POLAPLAST P12 and the EPDM 856 in granulometry of 0.5-1.5mm.**  
Applied by spraying machine.



Description	Consumption
POLAPLAST P10 - Polyurethane primer.	0.2kg/m <sup>2</sup>
<b>BASE LAYER</b>	
POLAPLAST P13 - One-component, polyurethane binder.	1.32kg/m <sup>2</sup> for 11mm mixture
RECYCLED RUBBER 858 in granulometry of 1-4mm.	6.6kg/m <sup>2</sup> for 11mm mixture
<b>SPRAY LAYER</b>	
POLAPLAST P12 - Colored, two-component polyurethane spray coating.	1.35kg/m <sup>2</sup>
EPDM 856 in granulometry of 0.5-1.5mm.	0.9kg/m <sup>2</sup>