

POLEPOX FLOOR 817

EPOXY-BASED, SELF-LEVELING, THREE COMPONENT FLOORING

GENERAL CHARACTERISTICS

POLEPOX FLOOR 817 is epoxy-based, self-leveling, three-component flooring.

- Creates colored, easy-to-clean flooring without joints, not requiring maintenance and meeting **health standards**.
- Resistant to acid solutions, alkalis, oil, grease, wastes.
- Prevents floorings from creating dust, strengthening their durability and resistance.
- Resistant to mechanical stresses, wearing from friction and chemical effects.
- It is ideal for covering floorings, mosaics, cement surfaces, decks, bio-cleanings.
- Areas of application: industries, food industries, professional kitchens, car workshops, parking areas, bio-cleanings, production plants, hospitals for antibacterial use etc.

TECHNICAL DATA

Basis:	two-component epoxy resin, aggregates
Appearance:	viscous liquid
Viscosity(A+B+C):	8000-17000 mPa•s at 25°C
Bulk Density (A+B+C):	1,572 ± 0,02 Kg/lit
Mixing proportion (A:B:C):	38:12:50 by weight
Granulometry (C):	160 μm - 500 μm
Application time:	approx. 30 min at 25°C
Final strength:	after 7 days at 25°C
Compressive strength (A+B+C): (ASTM D 695)	83.7 N/mm ² , 7 days at 25°C
Flexural strength (A+B+C): (Din 1164)	69.6 N/mm ² , 7 days at 25°C
Hardness according to SHORE D:	85 ± 3
Walkability:	after 3 days in thickness of 3mm at 25°C
Adhesive strength:	>3 N/mm ² (breaking of concrete)
Temperature for the application and drying of the material:	10 – 38°C
Colors:	available in 16 RAL colors and on request from RAL colors

KDF - Kataskeves Dapedon LTD

e : exports@kdf.gr w : www.kdf.gr

Showroom Office

1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office

19 Mitropoleos Str
54624, Thessaloniki, Greece



SUBSTRATE REQUIREMENTS

Concrete quality:	at least C20/25
Age:	at least 30 days
Moisture content:	below 4%

PREPARATION - APPLICATION

Applied only on dry surfaces. Protected from arising humidity and free of materials that might prevent bonding e.g. dust, loose particles, grease etc. The success in the application depends on the right preparation of the underlay and use of the material.

- Treatment of the surface with a mosaic machine, with sandblast or rotor machine, depending on the thickness of the final coating.
- **Good, dry** cleaning of the surface from dust and residues with vacuum cleaner and squeegees.
- Caution must be taken so that temperature of the substrate as well as ambient air remains above 10°C during application and curing of the materials while relative environment humidity does not exceed 75%.
- Priming of the surface with **POLEPOX-PR 824** in two or more layers. Then, application of one or more layers, with **POLEPOX-PR 824**, until the surface is saturated and a film is created. Consumption: 250-600 gr/m², depending on the absorption of the underlay.
- After hardening of the primer (2-12 hours depending on the ambient temperature) and within 24 hours, follows the application of **POLEPOX FLOOR 817**.
- Good mixing of components A (resin) & B (hardener) packed into separate containers in fixed weight proportions. Mixing should be performed using a low revolution mixer (300-600 rpm) for 1-2 min. Stirring of the mixture should be performed thoroughly near the sides and bottom of the container in order to achieve uniform dispersion of the hardener. Afterwards, the whole quantity of component C (quartz sand) is gradually added into the mixture under continuous stirring until a uniform epoxy mortar is formed.
- The epoxy mortar is poured on the floor and spread on the desired thickness using a notched trowel or special rolls.
- Following the application of the **POLEPOX FLOOR 817**, the self-leveling layer should be rolled using a special spiky-roller in order to release any possibly entrapped air and avoid the formation of bubbles.
- For the creation of a completely non-slip surface, it is recommended on a still fresh layer the dredging of dry, quartz sand with a particle size 0,1-0,4 mm or 0,4-0,8 mm depending on the desired anti-slipping effect. After hardening of **POLEPOX FLOOR 817**, any loose grains are being removed using a high suction vacuum cleaner. Finally a finishing layer of A+B components of **POLEPOX FLOOR 817** or **POLEPOX COAT 814** is applied for the creation of an acid proof, easy to clean, non-slip surface. Consumption: 0,8-1 kg/m².

CONSUMPTION

- 1,7 Kg/m²/mm,
 - 3 Kg/m²/1,8mm,
 - 4 Kg/m²/2,4mm.
-

APPLICATION TOOLS

Rubber rolls, notched trowel depending the desired thickness. Tools should be cleaned with solvent immediately after use.

PACKAGING

Supplied in packages of 36 kg (two drums, one bag). Components A,B and C have the fixed weight proportion.

STORAGE

One year in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30°C, protected from moisture and heat.

REMARKS

- Working time of **POLEPOX FLOOR 817** decreases when ambient temperature rises.
 - Prolonged storage of partially used containers must be avoided as contact with atmospheric moisture will result in skinning and clouding of the product.
 - Do not mix or apply unless surface, air and material temperatures are over 10°C during the next 24 hours.
 - Do not apply to floors if there is moisture in the subfloor drive or hydrostatic pressure. Prior precautions measurements of humidity with special device are suggested.
 - **POLEPOX FLOOR 817** will yellow upon prolonged exposure to sunlight or high-intensity artificial lights. A urethane topcoat is highly recommended for color stability.
 - In case old floors are going to be laid or a long period of time (12 hours for summer and 24 hours for winter) interferes between successive layers, the surface must be thoroughly cleaned and grinded prior to application of a new layer.
 - After hardening, **POLEPOX FLOOR 817** is completely safe for health and meets all requirements for food industries.
-

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the material safety data sheet.

KDF

Sports Flooring Systems & Building Materials
50 YEARS OF EXPERIENCE

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece

