

POLAPLAST P13

ONE-COMPONENT POLYURETHANE BINDER

GENERAL CHARACTERISTICS

POLAPLAST P 13 is a solvent free, clear, moisture curing one component polyurethane binder with good long term elasticity.

POLAPLAST P 13 exhibits excellent adhesion to most rubber granulates and gives a strong performance both in terms of tensile strength and durability. It is mixed with **RECYCLED RUBBER (858)** 1-4mm thickness for the creation of the **BASE COAT OF POLTRACK SYSTEM**, as well as for the base coat of playgrounds, tennis courts etc.

TECHNICAL DATA

Basis:	one-component polyurethane
Appearance:	liquid
Color:	transparent
Viscosity DIN 53018/1+2:	approx. 3200 mPa•s at 20°C
Density DIN 53217:	approx. 1,08 gr/cm ³ at 20°C
Temperature for the application and drying of the material:	10 – 35°C

PREPARATION-APPLICATION

Applied on dry surfaces, free of materials that might prevent bonding e.g. dust, loose particles etc (in case of asphalt or concrete). The success in the application depends on the right preparation of the underlay and use of the material.

- **Good, dry** cleaning of the surface from dust and residues.
- Priming of the surface with **POLAPLAST P10** applied by airless spray equipment or brush. The **BASE COAT OF POLTRACK SYSTEM** should be constructed while **POLAPLAST P10 is still sticky (wet in wet procedure)**. Curing takes place at ambient temperature by evaporation of the solvent and reaction with atmospheric moisture. High temperatures and moisture will shorten the cure time. Opened drums should be used up quickly.
- **The BASE COAT OF POLTRACK SYSTEM** should be constructed within 48 hours of primer application.
- Good mixing of the **POLAPLAST P13** and the **RECYCLED RUBBER 858 (see mixing ratio below)**. Mixing should be performed using a low revolution mixer (300-600 rpm) for 1-2 min. Stirring of the mixture should be performed thoroughly near the sides and

bottom of the container in order to achieve homogeneity.

- Following, the mixture is poured on the surface and spread on the thickness 11 to 12mm using a suitable paving machine or a hand straightedge. If the application will be done with hand straightedge then small irregularities in the surface may be removed by rolling the surface using a metallic cylinder.
- The temperature should not fall below 10°C during curing of **POLAPLAST P13**.
- Curing of **POLAPLAST P13** takes place at ambient temperature by reaction with atmospheric moisture. High temperatures and moisture will shorten the cure time of the **POLAPLAST P13**.
- The surface can be walked on after 12 – 18 hours at 20°C. After the surface is fully cured (depending on the temperature and humidity, the curing of the **BASE COAT OF POLTRACK** will take 12-48hours), follows the application of the final **TOP COATING OF THE POLTRACK SYSTEM**.

CONSUMPTION

1,08kg **POLAPLAST P13** combined with 6.1kg **RECYCLED RUBBER 858** 1-4mm thickness for 11-12mm base coat.

RATIO

15% **POLAPLAST P13** to 85% **RECYCLED RUBBER 858** 1-4mm.

APPLICATION TOOLS

A suitable paving machine or a hand straightedge.

If the application will be done with hand straightedge then small irregularities in the surface may be removed by rolling the surface using a metallic cylinder.

PACKAGING

Supplied in drums of 220 Kg. Other size on request.

STORAGE

One year in unopened containers in cool and dry places, out of sunlight, with minimum temperature 5°C and maximum temperature 30°C. Open drums should be used quickly.

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the material safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598
Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece

