

POLFLOOR-PU 807

GENERAL CHARACTERISTICS

POLFLOOR-PU 807 is polyurethane-based, anti-dust, colored, two-component resin.

- Creates colored, easy-to-clean indoor or outdoor floorings.
- Ideal for old and new surfaces, for light and middle circulation such as industrial, troweled floorings, mosaics, cement surfaces, workshops, and storehouses. Suitable even for metallic surfaces and for painting swimming pools.
- Provides permanent protection from U.V. radiation.
- Eliminates dust and decay from old & new floorings, reinforcing their durability.
- Offers high mechanical resistance and chemical protection against acid, alkalis, oil, and grease.
- Penetrates in depth, protects and hardens old absorbent cement surfaces.
- It can be easily repaired locally if necessary.

TECHNICAL DATA

Basis:	two-component polyurethane resin
Appearance:	liquid
Viscosity:	100-450 mPa•s at 25°C
Density:	0,94 ± 0,001 kg/l
Mixing proportion (A:B):	75:25 by weight
Final strength:	after 7 days at 25°C
Walkability:	after 2 days at 25°C
Adhesive strength:	>3 N/mm ² (breaking of concrete)
Colors:	16 colors in RAL codes.
Temperature for the application and drying of the material:	10 – 38°C

SUBSTRATE REQUIREMENTS

Concrete quality:	at least C20/25
Age:	at least 30 days
Moisture content:	below 4%

PREPARATION-APPLICATION

Applied only on dry surfaces. Protected from arising humidity and free of materials that might prevent bonding e.g. dust, loose particles, grease etc. The success in the application depends on the right preparation of the underlay and use of the material.

- Grinding of the surface with a mosaic machine, or sandblast and rotor machine in case of vertical surfaces.
 - **Good, dry** cleaning of the surface from dust and residues with vacuum cleaner and squeegees.
 - Caution must be taken so that temperature of the substrate as well as ambient air remains above 12°C during application and curing of the materials while relative environment humidity does not exceed 75%.
 - Good mixing of components A (resin) & B (hardener) packed into separate containers in fixed weight proportions. Mixing should be performed using a low revolution mixer (300-600 rpm) for 1-2 min. Stirring of the mixture should be performed thoroughly near the sides and bottom of the container in order to achieve uniform dispersion of the hardener.
 - In case of troweled surfaces when there is a need for a penetrating material, it is suggested the application of the **POLFLOOR-PU 807**, with dilution with 10-15% **POLYURETHANE SOLVENT** for deeper penetration, in one layer.
 - Then application of two or more layers with **POLFLOOR-PU 807** undiluted. The last layer is applied, until the surface is saturated and a film is created. If mat spots appear, then another layer is necessary until the surface is shiny. The next layer follows the other after the previous dries, within 6-12 hours depending on the ambient temperature and not more than 24 hours. The number of layers vary from one surface to another depending on the absorbency.
-

CONSUMPTION

300 gr/m², in three or more layers (including the primer layer) depending on the type, absorbency and roughness of the underlay.

APPLICATION TOOLS

Nappy rolls, brushes for smooth industrial surfaces. Tools should be cleaned with solvent immediately after use.

PACKAGING

Supplied in packages of 5kg and 15 kg (two drums). Components A and B have the fixed weight proportion.

STORAGE

One year in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30°C, protected from moisture and heat.

REMARKS

- Working time of **POLFLOOR-PU 807** decreases when ambient temperature rises.
 - Prolonged storage of partially used containers must be avoided as contact with atmospheric moisture will result in skinning and clouding of the product.
 - Do not mix or apply unless surface, air and material temperatures are over 12°C during the next 24 hours.
 - Do not apply to floors if there is moisture in the subfloor drive or hydrostatic pressure. Prior precautions measurements of humidity with special device are suggested.
 - It **cannot be applied in thickness for filling cracks or holes**.
 - In case of cracks or holes we recommend the use of **EPOFIX-H 207**. The usage of rotor machine must precede the application of **POLFLOOR-PU 807** for the creation of pores and the right penetration.
 - In case old floors are going to be laid or a long period of time interferes between successive layers, the surface must be thoroughly cleaned and grinded prior to application of a new layer.
 - After hardening **POLFLOOR-PU 807** is completely safe for health.
-

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the material safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.