

QUICKLAWN PLAYGROUND SANDPROOF with EPDM CLOSED POROUS SYSTEM



Innovative, elastic, seamless, flexible colored flooring, ideal for playground floorings.

It consists of a cushion base, with a first layer of a prefabricated, special, safety pad for playground flooring, **RAPIDFOAM 868**, followed by a layer of **PU PRIMER 870** with polyester net, and third layer a mixture of **EPDM** granules (granulometry 0.5-1.5mm) mixed with **PU BINDER 1178** in thickness of 15mm.

Then follows the modified sealing, sandproof and waterproof **KDF-PU 1055** pore filler with high elasticity in 2 crossing layers and the modified, **KDF-PU 1056**, sealing, UV-resistant, aliphatic, elastic, glossy top layer in 3 crossing layers.

It provides an excellent safety flooring with a very quick application in a variety of colors and closed pores. Playground flooring that is easy to be cleaned and maintained.

Steps:

1. **RAPIDFOAM 868** - Prefabricated special safety pad for playground floorings.

2. **PU PRIMER 870** - Special, polyurethane primer with a polyester net.

3. Mixture of **PU BINDER 1178** and **EPDM** granules in granulometry of 0.5-1.5mm.

Applied by flat metal trowel after spreading and leveling with rake and straightedge. Rolling with cylinder follows for compacting.

4. **KDF-PU 1055** - Polyurethane, modified, sandproof and waterproof, elastic pore filler.

Applied by metal trowels to create a completely non porous surface.

5. **KDF-PU 1056** - Polyurethane, modified, UV-resistant, aliphatic, elastic, glossy, two-component top coating.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece



Preparation – Application

Applied only on dry asphalt and concrete surfaces (over 30 days old from date of placement for asphalt and 40 days for concrete) without rising humidity issues and free of materials that might prevent bonding e.g. dust, loose particles, grease etc. The success in the application depends on the right preparation of the underlay and use of the material.

- **Good, dry** cleaning of the surface from dust and residues.
- Placement of the safety pads **RAPIDFOAM 868**.
- Priming of the surface with the special **POLYURETHANE PRIMER 870** in two layers. Consumption: 200-250 gr/m², depending on the absorption of the underlay. A polyester net is applied between the first and second layer of **PU PRIMER 870**.
- Follows the application with paver machine of a mixture of **PU BINDER 1178 with EPDM granules in granulometry 0.5-1.5mm** in thickness of 15mm.
- Afterwards when the surface of EPDM is dry, application of **polyurethane, modified, sandproof and waterproof, elastic pore filler KDF-PU 1055 with metal trowels to create a completely non porous surface with consumption 2 kg per square meter in 2 layers**.
- Before the last **UV-resistant top layers** are applied, the surface needs the use of sandpaper machine to make a completely even surface without any irregularities or loose crumbs.
- After the sandpaper of the whole surface is finished follows the application of 400 gr/square meter of our **polyurethane, modified, UV-resistant, aliphatic, elastic, glossy, two-component top coating KDF-PU 1056** in three cross layers by airless spray or by rollers.

Important Remarks

- ✓ During summer or during temperatures over 35 degrees, ideal time for the application of **QUICKLAWN SANDPROOF with EPDM** is between 21:00 and 09:00 and temperature less than 30°C, while in the winter, the minimum bearing temperature during application and drying should be over 10°C.
- ✓ The freshly coated surface should be protected from high temperatures, wind, rain and frost for at least the first 24 hours.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece



Substrate

Asphalt is the safer subfloor for sport floorings for sure and must be always preferred than concrete surfaces.

A.ASPHALT SUBSTRATE

The asphalt must have a slope of 0,7-1% **and must dry for at least 30 days so all solvents from the asphalt evaporate.**

The asphalt subfloor should be applied on well compacted 150 mm road base subfloor and asphalt should be laid in one layer (and not two) in 6 to 8 cm with fine and coarse aggregates (up to 15mm granulometry) like the kind of asphalt used in road construction.

So, new road-grade asphalt will have to be laid (minimum 60mm) in one layer containing coarse aggregates and then mature for 30 days at least, before any application takes place on top of the asphalt to avoid bubbles on the final layer of the sport or rubber floorings.

B. CONCRETE SURFACES

Concrete surface must be powerroweled and must be smooth with a slope of 0,7-1%.

Then concrete must dry at least for 40 days and then the application takes place if there is no arising humidity for the subfloor. Before the application takes place, there must **be a proper grinding** of the surface by a grinder machine to open the porous accordingly and also **a measurement by special instrument to measure humidity on the surface and in 10cm under the surface.**

Generally concrete is a risky subfloor and there may be problems **with arising humidity, especially in areas where the sea level is really high and when the sea is close.**

Always make expansion joints in large areas of concrete, in order to avoid uncontrollable cracks and failures.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece

