

POLAPLAST P10

POLYURETHANE PRIMER ONE-COMPONENT

GENERAL CHARACTERISTICS

POLAPLAST P10 is a low viscosity, moisture curing, clear, polyurethane-based, one-component primer with good long term elasticity. **POLAPLAST P10** is used as an adhesive component between the sub-floor and the base layer (wet-pour mixture of SBR and POLAPLAST P13) of KDF's running track systems.

- Designed for improving adhesion of base layer (wet-pour mixture) of KDF's running track systems on asphalt and concrete surfaces without rising humidity issues.
- Penetrates in depth.
- Ideal for old and new surfaces.

TECHNICAL DATA

Basis:	one-component polyurethane
Appearance:	liquid
Color:	transparent
Viscosity :	50 – 250 mPa•s at 25°C
Density :	0.9 – 1.0 Kg/Lt at 25°C
Temperature for the application and drying of the material:	10 – 40°C

PREPARATION-APPLICATION

Applied on dry surfaces without rising humidity issues, free of materials that might prevent bonding e.g. dust, loose particles, grease etc (in case of asphalt or concrete). The success in the application depends on the right preparation of the underlay and use of the material.

- **Good, dry** cleaning of the surface from dust and residues.
- Priming of the surface with **POLAPLAST P10** applied by airless sprayer equipment or brush, roller. The base layer (wet-pour mixture of SBR and **POLAPLAST P13**) of KDF's running track systems should be constructed while **POLAPLAST P10** is still a bit sticky. Curing takes place at ambient temperature by evaporation of the solvent and reaction with atmospheric moisture. High temperatures and moisture will shorten the cure time. **POLAPLAST P10** is applied in two or more layers as a thin film, and on the final layer, wet-pour mixture of SBR and **POLAPALST P13** can be applied on wet surface.
- The temperature should not fall below 10°C during curing.
- Opened drums should be used up quickly.
- Depending on the temperature and humidity, 3-5 hours is the minimum waiting time.
- The base layer (wet-pour mixture of SBR and **POLAPALST P13**) of the running track

systems should be constructed while the final layer of **POLAPLAST P10** is still sticky.

- **NOTE: Rain will cause the primer to lose its function! If the primer was affected by rain, the base layer should not be constructed! Instead, the sub floor has to dry and the primer application has to be repeated.**

CONSUMPTION

150-250 gr/m² depending on the type and the absorbency of the underlay.

APPLICATION TOOLS

Airless sprayer or brush or roller.

PACKAGING

Supplied in drums of 200 Kg.

STORAGE

12 months in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30°C (out of sunlight).

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

POLAPLAST P13

ONE-COMPONENT POLYURETHANE BINDER

GENERAL CHARACTERISTICS

POLAPLAST P13 is a solvent free, clear, moisture curing one component polyurethane binder with good long term elasticity.

POLAPLAST P13 exhibits excellent adhesion to most rubber granulates and gives a strong performance both in terms of tensile strength and durability. It is mixed with **RECYCLED RUBBER 858** for the creation of the base layer of KDF's running track systems as well as for the base coat of playgrounds, tennis courts etc.

TECHNICAL DATA

Basis:	one-component polyurethane
Appearance:	liquid
Color:	transparent
Viscosity :	4.000 – 8.000 mPa•s at 25°C
Density :	1.08 – 1.18 Kg / Lt at 25°C
Temperature for the application and drying of the material:	10 – 40 °C

PREPARATION-APPLICATION

Applied on dry surfaces, free of materials that might prevent bonding e.g. dust, loose particles etc (in case of asphalt or concrete). The success in the application depends on the right preparation of the underlay and use of the material.

- **Good, dry** cleaning of the surface from dust and residues.
- Priming of the surface with **POLAPLAST P10** applied by airless sprayer and brush. The the base layer of KDF's running track systems, wet-pour shock-absorbent mixture, should be constructed while **POLAPLAST P10 is still sticky (wet in wet procedure)**. Curing takes place at ambient temperature by evaporation of the solvent and reaction with atmospheric moisture. High temperatures and moisture will shorten the cure time. Opened drums should be used up quickly.
- Good mixing of **POLAPLAST P13** and **RECYCLED RUBBER 858 (see mixing ratio below)**. Mixing should be performed using a low revolution mixer (300-600 rpm) for 1-2 min. Stirring of the mixture should be performed thoroughly near the sides and bottom of the container in order to achieve homogeneity.
- Following, the mixture is poured on the surface and spread on in thickness from 11 to 12mm using a suitable paving machine or a hand straightedge and a flat trowel. Any small irregularities in the surface may be removed by rolling the surface using a metallic cylinder.
- The temperature should not fall below 10°C during curing of **POLAPLAST P13**.
- Curing of **POLAPLAST P13** takes place at ambient temperature by reaction with atmospheric moisture. High temperatures and moisture will shorten the cure time of the **POLAPLAST**

P13.

- The surface can be walked on after 12 – 18 hours at 25°C. After the surface is fully cured (depending on the temperature and humidity, the curing of the base layer mixture will take 12-48hours), follows the application of the final layers of the running track systems.
-

CONSUMPTION

1.32kg **POLAPLAST P13** mixed with 6kg **RECYCLED RUBBER 858** in granulometry of 0.5-2.5mm.

RATIO

18.3 % **POLAPLAST P13** to 81.7% **RECYCLED RUBBER 858** in granulometry of 0.5-2.5mm.

APPLICATION TOOLS

A suitable paving machine or a hand straightedge and a flat trowel.

PACKAGING

Supplied in drums of 220 Kg. Other size on request.

STORAGE

12 months in unopened containers in dry places, out of sunlight, with minimum temperature 5°C and maximum temperature 30°C.

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the material safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

SBR RUBBER GRANULES 858

GENERAL CHARACTERISTICS

It can be used in sports facilities as infill in synthetic grass with the parallel use of round sand and also as one of the components in case of cast applied wet-pour systems for playground floorings or as shock-pad for sport subfloors in athletic tracks and sports fields.

Rubber granule is derived from car and truck tires. During processing, the tires are mechanically granulated, removing all metal and synthetic fibers, as well as any other foreign part contained in there with specially designed sieves, so as to produce a 99.99% clear rubber with high quality.

PROPERTIES

- 100% recyclable
- Long life
- Resistance to adverse weather conditions
- High shock absorbency and vibration damping
- High abrasion resistance

PREPARATION-APPLICATION

In sports facilities and playgrounds to ensure flexibility of surface and vibration absorption.

TECHNICAL CHARACTERISTICS

Granulometry 1-3mm

DENSITY:	0.48kg/cm ³
SPECIFIC GRAVITY	1.20+/- .05 (Water = 1.0)
HARDNESS	60
HUMIDITY(%)	<0.65
ELASTICITY	100% - No change
RESISTANCE	113N/cm - Excellent

PACKAGING

Packaging is available in big-bags -1 ton in following sizes:

Grain size	0,5-1,5 mm
Grain size	0,5-2,5 mm
Grain size	0.5-4.0 mm
Grain size	2-8 mm
Grain size	8-20 mm
Grain size	80-50 mm
Grain size	80-120 mm

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece



ELASTOTURF NEUTRO

SPECIAL, ELASTIC, COATING FOR INTERNAL AND EXTERNAL SPORT FIELDS

GENERAL CHARACTERISTICS

ELASTOTURF NEUTRO is acrylic-based, elastic, colored, non-slip coating for external and internal sport fields.

- It can be combined with prefabricated shock-absorbent rolls in thickness 4-14mm or wet-pour mixtures.
- Ideal for basketball, volleyball, handball, football and tennis external courts. Suitable for sports centers, schools, fitness centers, pavements, hallways.
- Applied easily, having low cost.
- Provides a safe, high quality game.

TECHNICAL DATA

Basis:	one-component acrylic resin
Appearance:	viscous liquid
Colors:	neutral
Viscosity:	35.000 – 45.000 mPa•s at 25°C
Density:	1.75 – 1.85 Kg/Lt
Temperature for the application and drying of the material:	10 – 40°C after 24 hours
Walkability:	

PREPARATION-APPLICATION

Applied only on dry surfaces, without rising humidity issues and free of materials that might prevent bonding e.g. dust, loose particles, grease etc. The success in the application depends on the right preparation of the underlay and use of the material.

- **Good, dry** cleaning of the surface from dust and residues with vacuum cleaner and squeegees.
- Application of the material on prefabricated shock-absorbent rolls in thickness 4-12mm or a rubber mixture of **SBR plus PU BINDER**, for sealing the pores of the underlay and plasticize the surface.
- Depending on the ambient temperature, **ELASTOTURF NEUTRO** is diluted with 2-5% water, prior to application, in order to achieve better fluidity. The next layer follows the other after the previous dries.

CONSUMPTION

1.3 - 2.5 kg/m².

APPLICATION TOOLS

Special squeegees. Tools should be cleaned with **WATER** immediately after use.

PACKAGING

Supplied in barrels of 200 kg.

STORAGE

12 months in unopened containers in dry places with minimum temperature 5°C and high temperature 30°C (avoid sunlight).

REMARKS

- **ELASTOTURF NEUTRO** should be applied in layers smaller than 0.6-0.7mm in order to avoid cracks on the material, due to the rapid evaporation of water. Lining thickness more than 1mm is achieved only by repeated layers.
 - During summer, ideal time for the application of **ELASTOTURF NEUTRO (850)** is between 6:00-9:00 a.m. and temperature less than 30°C, while in the winter, the minimum bearing temperature during application and drying should be 10°C.
 - The freshly coated surface should be protected from high temperatures, wind, rain and frost for at least the first 24 hours.
 - In case it gets damaged, it is simply repaired and recoated on the spot.
-

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the material safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr



Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece

ELASTOTURF TRACK

GENERAL CHARACTERISTICS

ELASTOTURF TRACK is a highly pigmented 100% acrylic polymer concentrate, filled with colored EPDM rubber in fine granulometry. It is designed for use for **POLTRACK SPRAYCOAT ACRYLIC** System.

Ideal for making an older track look new, or to be used on new construction, **ELASTOTURF TRACK** provides a low cost solution.

TECHNICAL DATA

Basis:	one-component acrylic resin
Appearance:	viscous liquid
Colors:	neutral
Viscosity:	4.000 – 9.000 mPa•s at 25°C
Density:	1.44 – 1.54 Kg/Lt
Temperature for the application and drying of the material:	10 – 40°C after 24 hours
Walkability:	

PREPARATION-APPLICATION

- Application should be done with a spray coat machine.
- Substrate must be completely cured prior applying **ELASTOTURF TRACK**.
- After **ELASTOTURF NEUTRO** dries, follows the application of **ELASTOTURF TRACK** mixed with EPDM 0.5 -1.5 mm (mixing ratio 50:50 by weight).
- The application should take place in 2-3 layers.

CONSUMPTION

1-1.5kg/m² in two or three layers.

PACKAGING

150 Kg Barrels

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the material safety data sheet.

KDF

Sports Flooring Systems & Building Materials
50 YEARS OF EXPERIENCE

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece



EPDM 856

RUBBER GRANULES

GENERAL CHARACTERISTICS

Type of material: Rubber EPDM

Grain size: 0.8-2.5mm,1.0-3mm,1.0-4mm or others

PERFORMANCE OF SAMPLE 25%

Test item	Performance
Tensile strength (Mpa)	>4.3
Elongation at break (%)	>735
Hardness (shore A)	60-65
Specific gravity (kg/cm ³)	1.45 ± 0.05

PREPARATION-APPLICATION

EPDM 856 granules are basically used for wet pour colored playground floorings (granulometry 1-3mm), for flexible multipurpose outdoor courts in 10-20 mm, SYSTEM COLORFLEX, and in applications of running track system such as POLTRACK SANDWICH SYSTEM (granulometry 1-3mm) and POLTRACK SPRAYCOAT SYSTEM (granulometry 0.5-1.5 mm).

Can be used also as infill of artificial synthetic turf or in the production of epdm rubber tiles or even loose lay and around swimming pools as a flexible flooring.

REMARKS

- It is highly suggested (especially in hot climates like in Middle East countries) the usage of the UV-resistance top coat **POLYSPORT XP 1069**, which gives a strong UV protection and doesn't allow the change of color to occur. **POLYSPORT XP 1069** is produced in all EPDM colour range and needs to be applied with 0,4 kg/m² in two crossing layers by airless sprayer or rollers.
- In case that there is no usage of UV-resistance polyurethane aliphatic coating strong shades like blue, rose, orange, grey etc will alter.

KDF

Sports Flooring Systems & Building Materials

50 YEARS OF EXPERIENCE

- All technical data are correct to the best of our knowledge and are intended to help our customers.
 - They do not constitute a guarantee of qualities and provide on bases for legal liability.
 - We advise our customers to choose the PU-binder according to the type and color of the EPDM rubber granules.
-

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece

