



WORLD  
ATHLETICS™

# PRODUCT CERTIFICATE

World Athletics is pleased to certify that the following product meets all the technical requirements of the World Athletics Rules for the relevant competitions.

Product's Trade Name:

**Synthetic surface, Poltrack Full PU**

Description, Colour/Absolute Thickness:

**Full PUR, 15.0mm**

Company Name, Country:

**Kataskeves Dapedon Ltd. (KDF), GRE**

Catalogue Number:

-

Certification Number:

**S-20-0297**

Test Report by and on:

**No. 300620, Trackmaster(Thailand)Co. Ltd.(THA)  
30 June 2020**

Note:

-

Date of Issue:

**1 September 2020**

Date of Expiry:

**September 2024**

Issued in accordance with the terms and conditions of the World Athletics Certification System

**Jon Ridgeon**  
World Athletics CEO



Intertek Consumer Goods GmbH · Würzburger Straße 152 · 90766 Fürth · Germany

**KATASKEVES DAPEDON LTD - KDF**  
MRS. Maria Nikolaidoy  
Mitropoleos 19  
**54024 Thessaloniki**  
**GREECE**

Fürth, May 12/2020

**TEST REPORT No. FUTYP2020-01959-C**

Date sample received: March 06/2020  
Period of testing: March 19/2020 – April 29/2020  
Technical Director: Kerstin Scharrer

**Sample description: EPDM Granulates E1, E2, E7, E8, E11, E12, E13, E15, E16, E17, E18, E19, E20**



*For the test results please refer to next pages*

## Test order

Test of products for polycyclic aromatic hydrocarbons

Summary	Results
Further requirements	<i>pass</i>

### Sample description:

No. 1:	Granulate E1 (red rose)
No. 2:	Granulate E2 (orange)
No. 7:	Granulate E7 (brown)
No. 8:	Granulate E8 (dark brown)
No. 11:	Granulate E11 (light blue)
No. 12:	Granulate E12 (dark blue)
No. 13:	Granulate E13 (purple)
No. 15:	Granulate E15 (light grey)
No. 16:	Granulate E16 (dark grey)
No. 17:	Granulate E17 (light green)
No. 18:	Granulate E18 (blue)
No. 19:	Granulate E19 (light brown)
No. 20:	Granulate E20 (EPDM red 0,5-1,5 mm)

## Test results

Abbreviations:  
n.d. = not determinable (< LoQ)  
LoQ = limit of quantification

### 1. Polycyclic Aromatic Hydrocarbons according to US-EPA+ 2 EFSA PAH and according to Regulation (EC) No. 1907/2006 (REACH) Annex XVII No. 50

Test method: AfPS GS 2019:01 PAK (2019-05)  
Limit of quantification: 0.1 mg/kg

#### Test results in mg/kg

Parameter	CAS-No.	Sample No. 1	Sample No.2	Sample No. 7	Sample No. 8
1 Naphthalene	91-20-3	<b>0.26</b>	<b>0.14</b>	<b>0.14</b>	<b>0.18</b>
2 Acenaphthylene	208-96-8	n.d.	n.d.	n.d.	n.d.
3 Acenaphthene	83-32-9	n.d.	n.d.	n.d.	n.d.
4 Fluorene	86-73-7	<b>0.66</b>	<b>0.22</b>	<b>0.23</b>	<b>0.68</b>
5 Phenanthrene	85-01-8	<b>1.9</b>	<b>0.40</b>	<b>0.46</b>	<b>1.1</b>
6 Anthracene	120-12-7	<b>0.22</b>	n.d.	n.d.	n.d.
7 Fluoranthene	206-44-0	<b>0.39</b>	<b>0.14</b>	<b>0.18</b>	n.d.
8 Pyrene	129-00-0	n.d.	n.d.	<b>0.21</b>	n.d.
9 Benzo(a)anthracene	56-55-3	<b>0.23</b>	n.d.	n.d.	n.d.

Polycyclic Aromatic Hydrocarbons - continued

Test results in mg/kg

Parameter	CAS-No.	Sample No. 1	Sample No.2	Sample No. 7	Sample No. 8
10 Chrysene	218-01-9	<b>0.28</b>	n.d.	n.d.	n.d.
∑11+12 Benzo(b)fluoranthene + Benzo(j)fluoranthene	205-99-2 + 205-82-3	n.d.	n.d.	n.d.	n.d.
13 Benzo(k)fluoranthene	207-08-9	n.d.	n.d.	n.d.	n.d.
14 Benzo(e)pyrene	192-97-2	n.d.	n.d.	<b>0.21</b>	n.d.
15 Benzo(a)pyrene	50-32-8	n.d.	n.d.	n.d.	n.d.
16 Indeno(1,2,3-cd)pyrene	193-39-5	n.d.	n.d.	n.d.	n.d.
17 Dibenzo(a,h)anthracene	53-70-3	n.d.	n.d.	n.d.	n.d.
18 Benzo(ghi)perylene	191-24-2	n.d.	n.d.	n.d.	n.d.
<b>Sum 15 PAH</b>		<b>3.3<sup>b</sup></b>	<b>0.40<sup>b</sup></b>	<b>0.88<sup>b</sup></b>	<b>1.1<sup>b</sup></b>

<sup>a</sup> For summation according to AfPS GS 2019:01 PAK the following PAH are not included: Acenaphthylene, Acenaphthene, Fluorene

<sup>b</sup> Only contents from 0.2 mg/kg were used for summation.

Parameter	CAS-No.	Sample No. 11	Sample No. 12	Sample No. 13	Sample No. 15
1 Naphthalene	91-20-3	<b>0.34</b>	<b>0.30</b>	n.d.	n.d.
2 Acenaphthylene	208-96-8	n.d.	n.d.	n.d.	n.d.
3 Acenaphthene	83-32-9	n.d.	n.d.	n.d.	n.d.
4 Fluorene	86-73-7	<b>0.19</b>	n.d.	<b>0.32</b>	<b>0.21</b>
5 Phenanthrene	85-01-8	<b>0.87</b>	<b>0.61</b>	<b>0.65</b>	<b>0.53</b>
6 Anthracene	120-12-7	n.d.	n.d.	n.d.	n.d.
7 Fluoranthene	206-44-0	<b>0.25</b>	<b>0.16</b>	n.d.	<b>0.16</b>
8 Pyrene	129-00-0	n.d.	n.d.	n.d.	<b>0.15</b>
9 Benzo(a)anthracene	56-55-3	n.d.	n.d.	n.d.	n.d.
10 Chrysene	218-01-9	<b>0.15</b>	<b>0.12</b>	n.d.	n.d.
∑11+12 Benzo(b)fluoranthene + Benzo(j)fluoranthene	205-99-2 + 205-82-3	n.d.	n.d.	n.d.	n.d.
13 Benzo(k)fluoranthene	207-08-9	n.d.	n.d.	n.d.	n.d.
14 Benzo(e)pyrene	192-97-2	n.d.	n.d.	n.d.	n.d.
15 Benzo(a)pyrene	50-32-8	n.d.	n.d.	n.d.	n.d.
16 Indeno(1,2,3-cd)pyrene	193-39-5	n.d.	n.d.	n.d.	n.d.
17 Dibenzo(a,h)anthracene	53-70-3	n.d.	n.d.	n.d.	n.d.
18 Benzo(ghi)perylene	191-24-2	n.d.	n.d.	n.d.	n.d.
<b>Sum 15 PAH</b>		<b>1.5<sup>b</sup></b>	<b>0.91<sup>b</sup></b>	<b>0.65<sup>b</sup></b>	<b>0.53<sup>b</sup></b>

<sup>a</sup> For summation according to AfPS GS 2019:01 PAK the following PAH are not included: Acenaphthylene, Acenaphthene, Fluorene

<sup>b</sup> Only contents from 0.2 mg/kg were used for summation.

Polycyclic Aromatic Hydrocarbons - continued

Test results in mg/kg

Parameter	CAS-No.	Sample No. 16	Sample No. 17	Sample No. 18	Sample No. 19
1 Naphthalene	91-20-3	n.d.	n.d.	n.d.	n.d.
2 Acenaphthylene	208-96-8	n.d.	n.d.	n.d.	n.d.
3 Acenaphthene	83-32-9	n.d.	n.d.	n.d.	n.d.
4 Fluorene	86-73-7	n.d.	n.d.	<b>0.45</b>	n.d.
5 Phenanthrene	85-01-8	n.d.	<b>0.12</b>	<b>0.81</b>	<b>0.12</b>
6 Anthracene	120-12-7	n.d.	n.d.	n.d.	n.d.
7 Fluoranthene	206-44-0	n.d.	n.d.	n.d.	n.d.
8 Pyrene	129-00-0	n.d.	n.d.	n.d.	n.d.
9 Benzo(a)anthracene	56-55-3	n.d.	n.d.	n.d.	n.d.
10 Chrysene	218-01-9	n.d.	n.d.	n.d.	n.d.
Σ11+12 Benzo(b)fluoranthene + Benzo(j)fluoranthene	205-99-2 + 205-82-3	n.d.	n.d.	n.d.	n.d.
13 Benzo(k)fluoranthene	207-08-9	n.d.	n.d.	n.d.	n.d.
14 Benzo(e)pyrene	192-97-2	n.d.	n.d.	n.d.	n.d.
15 Benzo(a)pyrene	50-32-8	n.d.	n.d.	n.d.	n.d.
16 Indeno(1,2,3-cd)pyrene	193-39-5	n.d.	n.d.	n.d.	n.d.
17 Dibenzo(a,h)anthracene	53-70-3	n.d.	n.d.	n.d.	n.d.
18 Benzo(ghi)perylene	191-24-2	n.d.	n.d.	n.d.	n.d.
<b>Sum 15 PAH</b>		<b>n.d.<sup>b</sup></b>	<b>n.d.<sup>b</sup></b>	<b>0.81<sup>b</sup></b>	<b>n.d.<sup>b</sup></b>

<sup>a</sup> For summation according to AfPS GS 2019:01 PAK the following PAH are not included: Acenaphthylene, Acenaphthene, Fluorene

<sup>b</sup> Only contents from 0.2 mg/kg were used for summation.

Parameter	CAS-No.	Sample No. 20
1 Naphthalene	91-20-3	n.d.
2 Acenaphthylene	208-96-8	n.d.
3 Acenaphthene	83-32-9	n.d.
4 Fluorene	86-73-7	n.d.
5 Phenanthrene	85-01-8	n.d.
6 Anthracene	120-12-7	n.d.
7 Fluoranthene	206-44-0	n.d.
8 Pyrene	129-00-0	n.d.
9 Benzo(a)anthracene	56-55-3	n.d.
10 Chrysene	218-01-9	n.d.
Σ11+12 Benzo(b)fluoranthene + Benzo(j)fluoranthene	205-99-2 + 205-82-3	n.d.
13 Benzo(k)fluoranthene	207-08-9	n.d.
14 Benzo(e)pyrene	192-97-2	n.d.
15 Benzo(a)pyrene	50-32-8	n.d.
16 Indeno(1,2,3-cd)pyrene	193-39-5	n.d.
17 Dibenzo(a,h)anthracene	53-70-3	n.d.
18 Benzo(ghi)perylene	191-24-2	n.d.
<b>Sum 15 PAH</b>		<b>n.d.<sup>b</sup></b>

<sup>a</sup> For summation according to AfPS GS 2019:01 PAK the following PAH are not included: Acenaphthylene, Acenaphthene, Fluorene

<sup>b</sup> Only contents from 0.2 mg/kg were used for summation.

## Conclusion

The tested sample of the presented products “**EPDM Granulates E1, E2, E7, E8, E11, E12, E13, E15, E16, E17, E18, E19, E20**” conform to the EC-Regulation 1907/2006, Annex XVII No. 50.

**Remark**

Requirements acc. to AfPS GS 2019:01 PAK (Utilization for GS-mark from July 1<sup>st</sup>, 2020) and Regulation (EC) No. 1907/2006, Annex XVII No. 50

Parameter	Category 1	Category 2		Category 3		Limit value acc. to EC regulation 1907/2006, Annex XVII No. 50	
	Materials intended to be put into the mouth, or materials in toys according to Directive 2009/48/EC or materials in articles for use by children up to three years of age with prolonged skin contact (longer than 30s) when used as intended	Materials, not covered by category 1, with prolonged skin contact (longer than 30s) or repeated short-term skin contact when used as intended or in a foreseeable way		Materials, not covered by category 1 or category 2, with short-term skin contact (up to 30 s) when used as intended or in a foreseeable way		Toys, including activity toys, and childcare articles – Components rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity, under normal or reasonably foreseeable conditions of use	Articles shall not be placed on the market for supply to the general public, if any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity, under normal or reasonably foreseeable conditions of use
		a. Use by children	b. other consumer products	a. Use by children	b. other consumer products		
Benzo[a]pyrene mg/kg	< 0.2	< 0.2	< 0.5	< 0.5	< 1	0.5	1
Benzo[e]pyrene mg/kg	< 0.2	< 0.2	< 0.5	< 0.5	< 1	0.5	1
Benzo[a]anthracene mg/kg	< 0.2	< 0.2	< 0.5	< 0.5	< 1	0.5	1
Benzo[b]fluoranthene mg/kg	< 0.2	< 0.2	< 0.5	< 0.5	< 1	0.5	1
Benzo[j]fluoranthene mg/kg	< 0.2	< 0.2	< 0.5	< 0.5	< 1	0.5	1
Benzo[k]fluoranthene mg/kg	< 0.2	< 0.2	< 0.5	< 0.5	< 1	0.5	1
Chrysene mg/kg	< 0.2	< 0.2	< 0.5	< 0.5	< 1	0.5	1
Dibenzo[a,h]anthracene mg/kg	< 0.2	< 0.2	< 0.5	< 0.5	< 1	0.5	1
Benzo[ghi]perylene mg/kg	< 0.2	< 0.2	< 0.5	< 0.5	< 1	-	-
Indeno[1,2,3-cd]pyrene mg/kg	< 0,2	< 0.2	< 0.5	< 0.5	< 1	-	-
Phenanthrene, Pyrene, Anthracene, Fluoranthene, mg/kg	< 1 – Sum	< 5 – Sum	< 10 – Sum	< 20 – Sum	< 50 – Sum	-	-
Naphthalene mg/kg	< 1	< 2		< 10		-	-
Sum 15 PAH mg/kg	<1	< 5	< 10	< 20	< 50	-	-
<b>Evaluation</b>	-	-	-	-	-	<b>pass</b>	-

---

**General note:**

This report has been prepared for the titled project or named part thereof and should not be relied upon or used for any other project without an independent check being carried out as to its suitability and prior written authority of Intertek being obtained. Intertek accepts no responsibility or liability for the consequences of this document being used for a purpose other than the purposes for which it was commissioned. Any person using or relying on the document for such other purposes agrees, and will by such use or reliance be taken to confirm his agreement to indemnify Intertek for all loss or damage resulting therefrom. Intertek accepts no responsibility or liability for this document to any party other than the person by whom it was commissioned.

We would like to point out, that Intertek can't provide legally binding assessments referring to isolated cases. The individual legal advice in Germany is reserved to the legal advisory professions and a binding interpretation is subject to the court of justice.

Copying excerpts or otherwise reproducing parts of the test report is permitted only with the consent of the laboratory accepting the order. This report pertains only to the test item(s).

All testing requests are subject to our Terms and Conditions available on [www.intertek.com](http://www.intertek.com).

END OF REPORT

