

SMARTCOAT 880

REPAIRING ACRYLIC COLORED COATING/ FILLER FOR EXTERNAL ATHLETIC COURTS

GENERAL CHARACTERISTICS

SMARTCOAT 880 is acrylic-based, one-component, colored coating for external basketball, tennis, volleyball and handball courts.

- Applied on asphalt and cement surfaces for the creation of a sub floor for athletic courts that does not need maintenance.
- Smoothens and upgrades rough courts in two or more layers depending on the porosity of the flooring.
- Minimizes the cost of reparation of sports grounds.
- Applied easily without prior experience. Water can be added gradually up to 3% per weight.
- In case of athletic courts, **SMARTCOAT 880** should be covered next day with coating for sports grounds **SMART TOP 890**.

Provides:

- Safe game.
- Perfect bounce of the ball.
- Resistance to weather conditions.

TECHNICAL DATA

Basis:	one-component acrylic resin, fillers
Appearance:	viscous liquid
Colors:	24 colors according to our colorchart
Viscosity:	20.000-30.000 mPa•s at 25°C
Density:	1.64 - 1.74 Kg/Lt
Temperature for the application and drying of the material:	10 – 40°C after 24h at 25°C
Walkability:	

PREPARATION-APPLICATION

Applied only on dry surfaces. Protected from arising humidity and free of materials that might prevent bonding e.g. dust, loose particles, grease etc. The success in the application depends on the right preparation of the underlay and use of the material.

- **Good, dry** cleaning of the surface from dust and residues with vacuum cleaner and squeegees.

- Priming of the surface with joining resin **RITIVEX R LIQUID 1102** for the proper adhesion of the material. Application of one or more layers until the surface is saturated. Avoid the creation of puddles of the material. Consumption: 200 - 400 gr/m², depending on the absorption of the underlay.
- When the primer begins to dry (approximately 1 hour depending on the ambient temperature), follows the application of **SMARTCOAT 880**.
- **SMARTCOAT 880** is applied in two or more layers, depending on the desirable thickness and the roughness of the surface, by squeegee. Each new coating is applied after the previous one starts to dry.
- Depending on the ambient temperature **SMART TOP 890** is diluted with 5-10% water, prior to application, in order to achieve better fluidity.

CONSUMPTION

2 kg/m² in two layers, depending on the porosity of the surface.

APPLICATION TOOLS

Squeegee. Tools should be cleaned with **WATER** immediately after use.



PACKAGING

190Kg barrels, 25kg drums



STORAGE

One year in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30°C.

REMARKS

- In case of extremely rough and sharp cement or asphalt surfaces it is recommended grinding of the surface with a mosaic machine, sandblast or rotor machine before the application of **SMARTCOAT 880**.
- Application and drying of **SMARTCOAT 880** must take place during cool hours. During summer or in hot climates, ideal time for the application of the material is between 22:00-9:00 a.m. and the minimum bearing temperature during application and drying should be 10°C.
- The freshly coated surface should be protected from high temperatures, wind, rain and frost for at least the first 24 hours.
- Higher lining thickness is achieved with repeated layers.
- For covering cracks, or holes it is recommended the addition of 20-30% quartz sand to

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Headquarters/Showroom Office
19th km National Road Thessaloniki-Moudania
57001, Neo Rysio, Thessaloniki, Greece
t / f : +30 2310 829598



SMARTCOAT 880's weight (grain thickness from 0.3-0.5 mm).

- In case it gets damaged, it is simply repaired and recoated on the spot.
- In case **SMARTCOAT 880** needs a bit more workability, water can be added gradually up to 3% on the total mix.

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Headquarters/Showroom Office
19th km National Road Thessaloniki-Moudania
57001, Neo Rysio, Thessaloniki, Greece
t / f : +30 2310 829598

