

KDF

Sports Flooring Systems & Building Materials

50 YEARS OF EXPERIENCE

systems should be constructed while the final layer of **POLAPLAST P10** is still sticky.

- **NOTE: Rain will cause the primer to lose its function! If the primer was affected by rain, the base layer should not be constructed! Instead, the sub floor has to dry and the primer application has to be repeated.**

CONSUMPTION

150-250 gr/m² depending on the type and the absorbency of the underlay.

APPLICATION TOOLS

Airless sprayer or brush or roller.

PACKAGING

Supplied in drums of 200 Kg.

STORAGE

12 months in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30°C (out of sunlight).

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece



POLAPLAST P13

ONE-COMPONENT POLYURETHANE BINDER

GENERAL CHARACTERISTICS

POLAPLAST P13 is a solvent free, clear, moisture curing one component polyurethane binder with good long term elasticity.

POLAPLAST P13 exhibits excellent adhesion to most rubber granulates and gives a strong performance both in terms of tensile strength and durability. It is mixed with **RECYCLED RUBBER 858** for the creation of the base layer of KDF's running track systems as well as for the base coat of playgrounds, tennis courts etc.

TECHNICAL DATA

Basis:	one-component polyurethane
Appearance:	liquid
Color:	transparent
Viscosity :	4.000 – 8.000 mPa•s at 25°C
Density :	1.08 – 1.18 Kg / Lt at 25°C
Temperature for the application and drying of the material:	10 – 40 °C

PREPARATION-APPLICATION

Applied on dry surfaces, free of materials that might prevent bonding e.g. dust, loose particles etc (in case of asphalt or concrete). The success in the application depends on the right preparation of the underlay and use of the material.

- **Good, dry** cleaning of the surface from dust and residues.
- Priming of the surface with **POLAPLAST P10** applied by airless sprayer and brush. The the base layer of KDF's running track systems, wet-pour shock-absorbent mixture, should be constructed while **POLAPLAST P10 is still sticky (wet in wet procedure)**. Curing takes place at ambient temperature by evaporation of the solvent and reaction with atmospheric moisture. High temperatures and moisture will shorten the cure time. Opened drums should be used up quickly.
- Good mixing of **POLAPLAST P13** and **RECYCLED RUBBER 858 (see mixing ratio below)**. Mixing should be performed using a low revolution mixer (300-600 rpm) for 1-2 min. Stirring of the mixture should be performed thoroughly near the sides and bottom of the container in order to achieve homogeneity.
- Following, the mixture is poured on the surface and spread on in thickness from 11 to 12mm using a suitable paving machine or a hand straightedge and a flat trowel. Any small irregularities in the surface may be removed by rolling the surface using a metallic cylinder.
- The temperature should not fall below 10°C during curing of **POLAPLAST P13**.
- Curing of **POLAPLAST P13** takes place at ambient temperature by reaction with atmospheric moisture. High temperatures and moisture will shorten the cure time of the **POLAPLAST**

P13.

- The surface can be walked on after 12 – 18 hours at 25°C. After the surface is fully cured (depending on the temperature and humidity, the curing of the base layer mixture will take 12-48hours), follows the application of the final layers of the running track systems.
-

CONSUMPTION

1.32kg **POLAPLAST P13** mixed with 6kg **RECYCLED RUBBER 858** in granulometry of 0.5-2.5mm.

RATIO

18.3 % **POLAPLAST P13** to 81.7% **RECYCLED RUBBER 858** in granulometry of 0.5-2.5mm.

APPLICATION TOOLS

A suitable paving machine or a hand straightedge and a flat trowel.

PACKAGING

Supplied in drums of 220 Kg. Other size on request.

STORAGE

12 months in unopened containers in dry places, out of sunlight, with minimum temperature 5°C and maximum temperature 30°C.

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the material safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

SBR RUBBER GRANULES 858

GENERAL CHARACTERISTICS

It can be used in sports facilities as infill in synthetic grass with the parallel use of round sand and also as one of the components in case of cast applied wet-pour systems for playground floorings or as shock-pad for sport subfloors in athletic tracks and sports fields.

Rubber granule is derived from car and truck tires. During processing, the tires are mechanically granulated, removing all metal and synthetic fibers, as well as any other foreign part contained in there with specially designed sieves, so as to produce a 99.99% clear rubber with high quality.

PROPERTIES

- 100% recyclable
- Long life
- Resistance to adverse weather conditions
- High shock absorbency and vibration damping
- High abrasion resistance

PREPARATION-APPLICATION

In sports facilities and playgrounds to ensure flexibility of surface and vibration absorption.

TECHNICAL CHARACTERISTICS

Granulometry 1-3mm

DENSITY:	0.48kg/cm ³
SPECIFIC GRAVITY	1.20+/- .05 (Water = 1.0)
HARDNESS	60
HUMIDITY(%)	<0.65
ELASTICITY	100% - No change
RESISTANCE	113N/cm - Excellent

PACKAGING

Packaging is available in big-bags -1 ton in following sizes:

Grain size	0,5-1,5 mm
Grain size	0,5-2,5 mm
Grain size	0.5-4.0 mm
Grain size	2-8 mm
Grain size	8-20 mm
Grain size	80-50 mm
Grain size	80-120 mm

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece



POLYSPORT STUCCO 1050

POLYURETHANE, ELASTIC, TWO-COMPONENT PORE FILLER

GENERAL CHARACTERISTICS

POLYSPORT STUCCO 1050 is elastic solvent-free, two component polyurethane based sealant for outdoor sport surfaces.

POLYSPORT STUCCO 1050 has very good filling capacity and thixotropic properties. It has low fluidity feature with its filler structure can be easily applied. It provides strong and elastic filling after the reaction.

TECHNICAL DATA

Mixing Ratio	90.8 : 9.2 (By weight)
Density of mixture (25°C)	1.69-1.79 Kg/lt
Viscosity of mixture (25°C)	40.000-55.000 mPa•s at 25°C
Pot-life (25°C)	20-30 min at 25°C
Application temperature	Min 10 – 40 °C
Curing (25°C and %60 relative humidity)	After 24 hours
Color	Beige

PREPARATION-APPLICATION

Applied on dry surfaces without rising humidity issues, free of materials that might prevent bonding e.g. dust, loose particles, grease etc (in case of asphalt or concrete). The success in the application depends on the right preparation of the underlay and use of the material.

- **Good, dry** cleaning of the surface from dust and residues using vacuum cleaner and squeegees.
- It can be applied directly on top of surfaces, on a cast-in-situ cushion base layer of wet pour (SBR rubber granules mixed with polyurethane binder) or prefabricated roll, which have to be dry, load bearing, clean and free of loose and brittle particles and substances which impair adhesion such as oil, grease, paint or other contaminants.
- The A component should be thoroughly stirred to incorporate any slight separation, while continuing stirring the contents of the B component (hardener) should be added. Continue stirring until a homogeneous mix is obtained. The mixed material must be used within 20-30 minutes of mixing at 25°C The surface must be dry and clean from dust and residues. Application is done by flat metal trowel.

CONSUMPTION

1.25 - 3.7 kg/m², depends on the porosity of the substrate.

PACKAGING

250 kg barrels and drums.

STORAGE

One year in unopened containers in cool and dry places, out of sunlight, with minimum temperature 5°C and maximum temperature 30°C.

REMARKS

- Substrate must be dry, clean, and free from dust, grease and oil. Application must be done between 10°C - 40°C.
- In case the second layer of PU pore filler is applied after more than 24 hours of the application of the first one then the whole surface must be sanded by a special sanding machine. After that the second layer can be applied.

CAUTION

Harmful if swallowed. Seek immediately medical attention. Rubber gloves and safety glasses with side guards should be worn.

For more information consult the safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece



POLAPLAST P12

COLORED TWO-COMPONENT POLYURETHANE SPRAY COATING

GENERAL CHARACTERISTICS

POLAPLAST P12 is a low viscous, two component polyurethane spray coating with good long term elasticity. Meets IAAF standard, it is environment- friendly, flexible with high strength.

POLAPLAST P12 is used as the second basic spray layer mixed with EPDM rubber granules, for the "on site" production of KDF's running track systems, **POLTRACK SPRAYCOAT SYSTEM**.

TECHNICAL DATA

Mixing Ratio	86.58 % : 13.42 % (By weight)
Viscosity(25°C)	900-3000 mPa
Density of mixture (25°C)	1.54-1.64 kg/lit
Pot-life (25°C)	app. 30 min. at 25°C
Application temperature	10 – 40 °C
Curing (25°C and %60 relative humidity)	9-12 hours
Color	KDF PU colorchart

PREPARATION-APPLICATION

Applied on dry surfaces, free of materials that might prevent bonding e.g. dust, loose particles etc (in case of asphalt or concrete). The success in the application depends on the right preparation of the underlay and use of the material.

- Application of the primer **POLAPLAST P10** (please consult the TDS of **POLAPLAST P10**)
- Application of the **BASE COAT OF POLTRACK SYSTEM** with wet-pour made from the mixture of **POLAPLAST P13** and the **RECYCLED RUBBER 858** (please consult the TDS of **POLAPLAST P13**)
- After the surface is fully cured (the curing depends on the temperature and humidity, 12-48 h), follows the application of the final **TOP SPRAY COATING OF THE POLTRACK SYSTEM**, which is consisted by **POLAPLAST P12** and **EPDM** granules of 0.5-1.5 mm granulometry
- Transportation and prolonged storage of spray coatings containing more than one pigment (e.g. beige or grey) can lead to separation of pigments. To obtain a uniform color, the spray coatings should be mixed well prior to application, in order to ensure an even color. The mixing must be done thoroughly until all the **EPDM** granules are coated. The mixing time with an agreed mixer will last from 3 to 5 minutes. The right spray viscosity depends on the

KDF - Kataskeves Dapedon LTD

e : exports@kdf.gr w : www.kdf.gr

Showroom Office

1 Papanikolaou Ave, Pefka

57010, Thessaloniki, Greece

t / f : 0030 2310 829598

Accounting Office

19 Mitropoleos Str

54624, Thessaloniki, Greece



spray equipment. Additional solvent amount (Xylene, Butylacetate) up to 2 % can be added to the mixture **POLAPLAST P12** and **EPDM**

- The **EPDM** granules must be dry
- The two components of **POLAPLAST P12** are thoroughly mixed at site. The **EPDM** granules and the **POLAPLAST P12** are mixed and applied with a suitable spraying machine Then the **TOP SPRAY COATING OF THE POLTRACK SYSTEM** is applied it two "cross hatch" layers. The curing time of the **TOP SPRAY COATING OF THE POLTRACK SYSTEM** is 9-12 hours. After this time, the second layer can be applied.
- **The second layer has to be applied "cross hatch", i.e. perpendicular to the first layer to insure a good coverage.**
- Curing takes place at ambient temperature and is influenced by atmospheric moisture. Higher temperatures and moisture will shorten the cure time. After 3-5 days, the **TOP SPRAY COATING OF THE POLTRACK SYSTEM** is fully cured.

CONSUMPTION

- Consumption of **POLAPLAST P12**: 1.35kg/m²
- Consumption of mixture of the **TOP SPRAY COATING OF THE POLTRACK SYSTEM (POLAPLAST P12 plus EPDM 0.5-1.5mm thickness, two layers)**: 2.25kg/m².

RATIO

60:40 **POLAPLAST P12** : **EPDM 0.5-1.5mm** (By weight)

APPLICATION

Spraying machine.

TOOLS

PACKAGING

Supplied in barrels.

STORAGE

12 months in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30°C (out of sunlight).

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD

e : exports@kdf.gr w : www.kdf.gr

Showroom Office

1 Papanikolaou Ave, Pefka

57010, Thessaloniki, Greece

t / f : 0030 2310 829598

Accounting Office

19 Mitropoleos Str

54624, Thessaloniki, Greece



EPDM 856

RUBBER GRANULES

GENERAL CHARACTERISTICS

Type of material: Rubber EPDM

Grain size: 0.8-2.5mm,1.0-3mm,1.0-4mm or others

PERFORMANCE OF SAMPLE 25%

Test item	Performance
Tensile strength (Mpa)	>4.3
Elongation at break (%)	>735
Hardness (shore A)	60-65
Specific gravity (kg/cm ³)	1.45 ± 0.05

PREPARATION-APPLICATION

EPDM 856 granules are basically used for wet pour colored playground floorings (granulometry 1-3mm), for flexible multipurpose outdoor courts in 10-20 mm, SYSTEM COLORFLEX, and in applications of running track system such as POLTRACK SANDWICH SYSTEM (granulometry 1-3mm) and POLTRACK SPRAYCOAT SYSTEM (granulometry 0.5-1.5 mm).

Can be used also as infill of artificial synthetic turf or in the production of epdm rubber tiles or even loose lay and around swimming pools as a flexible flooring.

REMARKS

- It is highly suggested (especially in hot climates like in Middle East countries) the usage of the UV-resistance top coat **POLYSPORT XP 1069**, which gives a strong UV protection and doesn't allow the change of color to occur. **POLYSPORT XP 1069** is produced in all EPDM colour range and needs to be applied with 0,4 kg/m² in two crossing layers by airless sprayer or rollers.
- In case that there is no usage of UV-resistance polyurethane aliphatic coating strong shades like blue, rose, orange, grey etc will alter.

KDF

Sports Flooring Systems & Building Materials

50 YEARS OF EXPERIENCE

- All technical data are correct to the best of our knowledge and are intended to help our customers.
 - They do not constitute a guarantee of qualities and provide on bases for legal liability.
 - We advise our customers to choose the PU-binder according to the type and color of the EPDM rubber granules.
-

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Showroom Office
1 Papanikolaou Ave, Pefka
57010, Thessaloniki, Greece
t / f : 0030 2310 829598

Accounting Office
19 Mitropoleos Str
54624, Thessaloniki, Greece

