



# KDF

Sports Flooring Systems & Building Materials  
**50 YEARS OF EXPERIENCE**

- Material coverage lies between 2.2 - 2.5 Kg/m<sup>2</sup> for a standard sandwich system and the material consumption depends on the temperature of substrate, ambience and material. Substrate temperatures must not exceed 50°C as this would liquefy the material.
- During the first hours after application, the coating had to be protected from direct contact with water, as this could cause foaming of the material. In case of (expected) rain, **POLAPLAST P20** should not be applied.
- NOTE: In cases re-coating is required, proceed in the first 24 hours after previous application without the use of primer if the surface is dry and clean.

## CONSUMPTION

2.2 - 2.5 kg/m<sup>2</sup>.

## APPLICATION TOOLS

V-notch trowel, 5.5 mm & spiked roller.



## PACKAGING

Supplied in barrels and drums(set).



## CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

**For more information consult the safety data sheet.**

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

**KDF - Kataskeves Dapedon LTD**  
e : [exports@kdf.gr](mailto:exports@kdf.gr) w : [www.kdf.gr](http://www.kdf.gr)

**Showroom Office**  
1 Papanikolaou Ave, Pefka  
57010, Thessaloniki, Greece  
t / f : 0030 2310 829598

**Accounting Office**  
19 Mitropoleos Str  
54624, Thessaloniki, Greece

