
# KDF

# POLEPOX DECOR INDOOR DECORATIVE FLOORING



kdf.gr

**KDF LTD** (www.kdf.gr) is one of the most dynamic and export-oriented Greek companies (currently activated in more than 70 countries in 4 continents), based in Greece(EU) and U.A.E too, with production facilities and warehouses in both countries for acrylic and polyurethane materials.

We are experts in sports, industrial and decorative flooring products and systems, with huge experience in Europe, Africa, Asia, Middle East and India as well.

Our export horizon is expanding rapidly and our goal is to stand out as a model of flexibility and competitiveness. The company, being one of the pioneer companies in the sector of sports flooring systems and building materials and giving particular attention to providing a fully upgraded range of products and services, provides certified systems by **ITF, IAAF, EU norms, LNE, LABOSPORT, ISASPORT, to name but a few.** 

#### Our systems are approved in many ministries like:

-Ministry of Education in U.A.E

-Ministry of Education in K.S.A

-Ministry of Education in Oman

-Ministry of Education in Kuwait and many other institutes like

-Oman Royal Police

-Aramco, K.S.A

-Musanada in U.A.E

-Municipality of Doha

-Municipality of Dubai, Abu Dhabi, Sharjah and many others institutions.

KDF goes far beyond trade, providing consultancy in marketing and also technical support all the way, from the costing till the finalization of the project. Operating under the requirements of ISO 9001/2015 for production, trade and also application, we make sure our products are first applied successfully at site by our own people before we launch them abroad.

Therefore, our systems have all stood the real life test in different climates, from Middle East till Russia, and this is one of our main assets, enabling us to provide full and vertical technical support from specifying to final application plus supervision when required or even full application and costing.

#### We invite you to discover a world of sports flooring expertise and solutions.



# **PHOTOGRAPH OF PROJECTS**





## **TECHNICAL DESCRIPTION**

#### POLEPOX DECOR

Indoor Decorative Flooring



Epoxy-based, unique, self-leveling, three-component decorative flooring with special metallic pigments to create a brilliant, vivid, one-of-a-kind floor. Can be customized to produce unique, metallic-look, light-reflective floors.

Recommended for commercial, business and recreational areas like conference halls, night clubs, hotels, restaurant, beach bars, shops, malls, show rooms, medical facilities, kitchen counters.

#### **Preparation – Application**

Applied only on dry, smooth concrete or other porous, stable surfaces like marble without arising humidity issues and free of materials that might prevent bonding e.g. dust, loose particles, grease etc. The success in the application depends on the right preparation of the underlay and use of the material.


- > Good, dry cleaning of the surface from dust and residues with vacuum cleaner and squeegees.
- Priming of the surface with POLEPOX-PR 824. Consumption: 200-300 gr/m<sup>2</sup> in two or more layers on industrial, troweled floorings, depending on the type and the absorbency of the underlay.
- After hardening of the primer (2-12 hours depending on the ambient temperature) and mixing the two components of EPODECOR 812, pour the mixed epoxy on the floor using a flat metal trowel for the application of the mixture. Move the trowel in crescents (half-circles) to create the unique POLEPOX DECOR patterns (or whatever else you might choose). Use the trowel gently and smoothly to apply the DECOR mix. Because of the unique appearance of KDF POLEPOX DECOR, the film thickness and

finishing techniques will have an impact on the final appearance of the floor, with the most dramatic effects occurring when the pigments are allowed to migrate with the film. Other special effects can be created spritzing the surface, during the application, with denatured alcohol and using compressed air, squeegees and other methods.

Finally, after POLEPOX DECOR has dried apply the clear topcoat, PLASTICOAT 850, if using the denatured alcohol and compressed air.

Colors: Following colorchart

# COLORCHART



The colors may vary slightly from the original due to digital representation.

## POLEPOX-PR 824

#### TRANSPARENT, EPOXY-BASED RESIN, USED AS AN ADHESIVE COMPONENT BETWEEN CONCRETE SURFACES AND EPOXY COATINGS

#### GENERAL CHARACTERISTICS

**POLEPOX-PR 824** is a clear, epoxy, two-component resin, which is used as an adhesive component between concrete surfaces and final epoxy coatings.

- Penetrates in depth.
- Eliminates dust from decay in old & new floorings, reinforcing their durability.
- Offers high mechanical resistance and chemical protection against acid solutions, alkalis, oil, grease etc.
- It can be easily repaired locally if necessary, but must precede grinding of the surface with a sandpaper or mosaic machine.

TEOLINICAL DATA	Desiet		
TECHNICAL DATA	Basis:	two-component epoxy resin	
	Appearance:	liquid	
	Colors:	transparent	
	Viscosity (A+B):	20-100 mPa s at 25°C	
	Density (A+B):	0,95-10,5 kg/lt	
	Mixing proportion (A:B):	50:50 by weight	
	Application time:	approx. 1 h at 25ºC	
	Final strength:	after 7 days at 25ºC	
	Walkability:	after 2 days	
	Adhesive strength:	>3 N/mm <sup>2</sup> (breaking of concrete)	
	Temperature for the application and drying of the material:	14 – 38°C	
SUBSTRATE	Concrete quality:	at least C20/25	
REQUIREMENTS	Age:	at least 30 days	
	Moisture content:	below 4%	
PREPARATION - APPLICATION		ed from arising humidity and free of materials that particles, grease etc. The success in the application nderlay and use of the material.	
	<ul> <li>Treatment of the surface with a mosaic machine, or with sandblast or rotor machine, depending on the thickness of the final coating.</li> </ul>		
	<ul> <li>Good, dry cleaning of the surface from dust and residues with vacuum cleaner and use of squeegees.</li> </ul>		
	<ul> <li>Caution must be taken so that temperature of the substrate as well as ambient air remains above 12°C during application and curing of the materials while relative environment humidity does not exceed 75%.</li> </ul>		
	<ul> <li>Good mixing of components A (resin) &amp; B (hardener) packed into separate containers in fixed weight proportions. Mixing should be performed using a low revolution mixer (300- 600 rpm) for 1-2 min. Stirring of the mixture should be performed thoroughly near the sides</li> </ul>		

	and Good mixing of components A (resin) & B (hardener) packed into separate containers in fixed weight proportions.		
	<ul> <li>In case of troweled surfaces when there is a need for a penetrating material, it is suggested the application of the <b>POLEPOX-PR 824</b> in two or more layers.</li> </ul>		
	- Then, application of one or more layers, with <b>POLEPOX-PR 824</b> , until the surface is saturated and a film is created. If mat spots appear, then another layer is necessary. The next layer follows the other before the previous starts to dry. The number of layers vary from one surface to another depending on the absorbency.		
CONSUMPTION	250-600 gr/m <sup>2</sup> in two layers depending on the type and the absorbency of the underlay.		
APPLICATION TOOLS	Nappy rolls, brushes, squeegees for smooth industrial surfaces. Tools should be cleaned with solvent immediately after use.		
PACKAGING	Supplied in packages of 30 Kg (two drums). Components A and B have the fixed weight proportion.		
<u>STORAGE</u>	One year in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30°C, protected from moisture and heat.		
REMARKS	- Working time of <b>POLEPOX-PR 824</b> decreases when ambient temperature rises.		
	<ul> <li>Prolonged storage of partially used containers must be avoided as contact with atmospheric moisture will result in skinning and clouding of the product.</li> </ul>		
	<ul> <li>It cannot be applied in thickness for filling cracks or holes. In this case it can only be used if mixed with fine dry sand.</li> </ul>		
	<ul> <li>Do not mix or apply unless surface, air and material temperatures are over 12°C during the next 24 hours.</li> </ul>		
	<ul> <li>Do not apply to floors if there is moisture in the subfloor drive or hydrostatic pressure. Prior precautions measurements of humidity with special device are suggested.</li> </ul>		
	- The usage of mosaic machine must precede the application of <b>POLEPOX-PR 824</b> for the creation of pores and the right penetration of the material.		

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

#### For more information consult the material safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

## POLEPOX DECOR

#### <u>GENERAL</u> CHARACTERISTICS

**KDF POLEPOX DECOR** is an indoor, epoxy-flooring system that can be customized to produce unique, metallic-look, light reflective floors. **POLEPOX DECOR** pigments are colored blends of nanoparticle pigments that are pre-measured, with no limit for creating brilliant, vivid, one-of-a-kind floors.

#### TECHNICAL DATA

Basis: epoxy resin Appearance: viscous liquid Viscosity: 3500-7000 mPa•s at 25°C Bulk Density: 1,19-1,29 Kg/lt Mixing proportion (A:B): 75:25 by weight Final strength: after 7 days at 25°C Walkability: after 2 days at 25°C Adhesive strength: >3 N/mm<sup>2</sup>(breaking of concrete) Colors: available in 13 colors

SUBSTRATE	Concrete quality:	at least C20/25
<u>REQUIREMENTS</u>	Age:	at least 30 days
	Moisture content:	below 4%

#### PREPARATION-APPLICATION

Ideal for restaurants, kitchens, cafeterias, retail or commercial floors, malls, garages and service areas, showrooms, hotel lobbies and entryways, medical facilities, arcades.

Applied only on dry surfaces. Protected from arising humidity and free of materials that might prevent bonding e.g. dust, loose particles, grease etc. The success in the application depends on the right preparation of the underlay and use of the material.

- Treatment of the surface with a mosaic machine.
- **Good**, **dry** cleaning of the surface from dust and residues with vacuum cleaner and use of squeegees.
- Caution must be taken so that temperature of the substrate as well as ambient air remains above 12°C during application and curing of the materials while relative environment humidity does not exceed 75%.
- Priming of the surface with POLEPOX-PR 824. Consumption: 200-300 gr/m<sup>2</sup> in two or more layers on industrial, troweled floorings. 300-600gr/m<sup>2</sup> depending on the type and the absorbency of the underlay.
- After hardening of the primer (2-12 hours depending on the ambient temperature) and mixing the two components of EPODECOR 812, pour the mixed epoxy on the floor using a flat metal trowel for the application of the mixture. Move the trowel in crescents (halfcircles) to create the unique POLEPOX DECOR patterns (or whatever else you might choose). Use the trowel gently and smoothly to apply the EPODECOR mix. Because of the unique appearance of KDF POLEPOX DECOR, the film thickness and finishing techniques will have an impact on the final appearance of the floor, with the most dramatic effects occurring when the pigments are allowed to migrate with the film. Other

	special effects can be created spritzing the surface, during the application, with	
	<ul> <li>denatured alcohol and using compressed air, squeegees and other methods.</li> <li>Finally, after EPODECOR 812 has dried apply the clear topcoat, PLASTICOAT 850, if using the denatured alcohol and compressed air.</li> </ul>	
<u>CONSUMPTION</u>	1,5 kg/m².	
APPLICATION TOOLS	Flat metal trowel, special rollers and squeegee. Tools should be cleaned with solvent immediately after use.	
<u>STORAGE</u>	One year in unopened containers in dry places with minimum temperature 5°C and maximum temperature 35 °C, protected from moisture and heat.	
REMARKS	<ul> <li>Application equipment, method and temperature will have a significant effect on coverage rates.</li> <li>Prolonged storage of partially used containers must be avoided as contact with atmospheric</li> </ul>	
	<ul> <li>moisture will result in skinning and clouding of the product.</li> <li>KDF POLEPOX DECOR floors can create unique effects, but while the process is simple, some practice is required to develop the best application techniques.</li> </ul>	
	<ul> <li>Do not mix or apply unless surface, air and material temperatures are over 12°C during the next 24 hours.</li> </ul>	
	<ul> <li>Do not apply KDF POLEPOX DECOR to floors if there is moisture vapor drive or hydrostatic pressure. Prior precautions measurements of humidity with special device are suggested.</li> </ul>	
	<ul> <li>KDF POLEPOX DECOR will yellow upon prolonged exposure to sunlight or high-intensity artificial lights. A urethane topcoat is highly recommended for color stability.</li> </ul>	
	<ul> <li>Although epoxy coatings are chemically resistant, the surface may stain after contact with some chemicals. A urethane coating is highly recommended to protect the surface.</li> </ul>	
CAUTION	The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided. Otherwise wash carefully with soap and water.	

#### For more information consult the material safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

## PLASTICOAT 850

GENERALPLASTICOAT 850 is an epoxy-based, clear, two-component coating and it is used for sealing<br/>and plasticizing decorative floorings and for the creation of 3D floorings.

It is applied in thickness up to 3mm giving the ability to insert small thin objects like coins, colored granules, flakes, 3D images etc.

Creates clear, glossy, easy-to-clean flooring without joints, not requiring maintenance.

TECHNICAL DATA	Basis:	two-component epoxy resin
	Appearance:	liquid
	Viscosity:	400-900 mPa s at 25ºC
	Density:	0,98 – 1.08 kg/lt
	Mixing proportion (A:B):	63:37 % by weight
	Final strength:	after 7 days at 25ºC
	Walkability:	after 2 days at 25ºC
	Adhesive strength:	>3 N/mm <sup>2</sup> (breaking of concrete)
	Colors:	clear
	Temperature for the application and drying of the material:	15 – 40° C

#### PREPARATION-APPLICATION

Applied only on dry surfaces. Protected from rising humidity and free of materials that might prevent bonding e.g. dust, loose particles, grease etc. The success in the application depends on the right preparation of the underlay and use of the material.

Recommended for hotels, exhibitions, showrooms and generally in areas where high aesthetic is required.

- Caution must be taken so that temperature of the substrate as well as ambient air remains above 15° C during application and curing of the materials while relative environment humidity does not exceed 75%.
- For the creation of the desired pattern, on the epoxy layer such as POLEPOX METALLIC, DECOQUARTZ SMOOTH, POLEPOX DÉCOR, EPOXY DESIGN etc, follows placement of the decorative material.
- After hardening any loose material is being removed using a vacuum cleaner, and within 24 hours, follows the application of **EPOXY PLASTICOAT 850**.
- Good mixing of components A (resin) & B (hardener) packed into separate containers in fixed weight proportions. Mixing should be performed using a low revolution mixer (300-600

rpm) for 1-2 min. Stirring of the mixture should be performed thoroughly near the sides and bottom of the container in order to achieve uniform dispersion of the hardener.	
- The epoxy mixture is poured on the floor and spread using notched trowel. The tool which is to be used depends on the desirable thickness.	
1.0-1.3 kg/m <sup>2</sup> (when the material is applied with V-Notched trowel (3.5 mm)	
V-Notched trowel (3.5mm) or squeegees (depending on the application). Tools should be cleaned with solvent immediately after use.	
Set of 13kg or barrels.	
One year in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30°C, protected from moisture and heat (avoid sunlight).	
Prolonged storage of partially used containers must be avoided as contact with atmospheric moisture will result in skinning and clouding of the product.	
The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water. For more information consult the safety data sheet.	

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.